



GENERAL PRODUCT SPECIFICATION

Item No.	BM30
-----------------	-------------

Date	9/22/08	Replaces	8/28/06	No. Pages	1
-------------	---------	-----------------	---------	------------------	---

Product Description:

Style	Blanket Roll w/design printing; perforated 15" center & 15" across".
Item Size (each)	30"wide x 150"long
Color	Gray Camo [Printed spunbond coverstock side to be wound on the inside]
Composition	>98% Polypropylene, <2% Color and Surfactant
Structure	A bi-laminate non-woven mat of randomly oriented meltblown micro-fibers [2-10 micron diameters] One side having a gray lint & abrasion resistant spunbond cover-stock (non-woven, continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters]). The (2) plies are secured together with bonded dimpling.
Technology	Meltblown, Spunbond
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Abrasion Resistant, Lint Resistant, & Chemical Resistant Universal Sorbent for Water-Based, Oil or Solvent Base Liquids- for various length uses.
-----------------------------	--

Absorbency Capacity	52 gal. per bale (saturated; medium viscosity-12.5x)
----------------------------	--

Packaging Description: (Fold and tape one corner of each roll to display printed spunbond design)

Package configuration	Case	Pkg. Weight	34.5-lbs (29)
Items per Package	1-Roll / Case	Pkg. Dimensions	17" x 17" x 31" H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	390	39
Caliper	SPCTM-003A	mils	160	10
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
3" Tensile Strength	SPCTM-006	lbs	38	3
Color	Visual	-----	Gray + Printing	per standard

The above properties are "nominal" values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.